

FORM PTO-1390 (Modified) (REV 11-2000)		U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE	ATTORNEY'S DOCKET NUMBER 219861US0PCT
TRANSMITTAL LETTER TO THE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US) CONCERNING A FILING UNDER 35 U.S.C. 371			U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR 10/049623
INTERNATIONAL APPLICATION NO. PCT/JP00/05510	INTERNATIONAL FILING DATE 17 August 2000	PRIORITY DATE CLAIMED 24 August 1999 (earliest)	
TITLE OF INVENTION WATER-CONTAINING POWDER COMPOSITION, PROCESS FOR PRODUCING THE SAME, AND COSMETIC PREPARATION CONTAINING THE POWDER COMPOSITION			
APPLICANT(S) FOR DO/EO/US TANAKA Yoichiro et al.			
Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:			
<ol style="list-style-type: none"> 1. <input checked="" type="checkbox"/> This is a FIRST submission of items concerning a filing under 35 U.S.C. 371. 2. <input type="checkbox"/> This is a SECOND or SUBSEQUENT submission of items concerning a filing under 35 U.S.C. 371. 3. <input checked="" type="checkbox"/> This is an express request to begin national examination procedures (35 U.S.C. 371(f)). The submission must include items (5), (6), (9) and (24) indicated below. 4. <input checked="" type="checkbox"/> The US has been elected by the expiration of 19 months from the priority date (Article 31). 5. <input checked="" type="checkbox"/> A copy of the International Application as filed (35 U.S.C. 371 (c) (2)) <ol style="list-style-type: none"> a. <input type="checkbox"/> is attached hereto (required only if not communicated by the International Bureau). b. <input checked="" type="checkbox"/> has been communicated by the International Bureau. c. <input type="checkbox"/> is not required, as the application was filed in the United States Receiving Office (RO/US). 6. <input checked="" type="checkbox"/> An English language translation of the International Application as filed (35 U.S.C. 371(c)(2)). <ol style="list-style-type: none"> a. <input checked="" type="checkbox"/> is attached hereto. b. <input type="checkbox"/> has been previously submitted under 35 U.S.C. 154(d)(4). 7. <input checked="" type="checkbox"/> Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371 (c)(3)) <ol style="list-style-type: none"> a. <input type="checkbox"/> are attached hereto (required only if not communicated by the International Bureau). b. <input type="checkbox"/> have been communicated by the International Bureau. c. <input type="checkbox"/> have not been made; however, the time limit for making such amendments has NOT expired. d. <input checked="" type="checkbox"/> have not been made and will not be made. 8. <input type="checkbox"/> An English language translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)). 9. <input checked="" type="checkbox"/> An oath or declaration of the inventor(s) (35 U.S.C. 371 (c)(4)). 10. <input checked="" type="checkbox"/> An English language translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371 (c)(5)). 11. <input type="checkbox"/> A copy of the International Preliminary Examination Report (PCT/IPEA/409). 12. <input checked="" type="checkbox"/> A copy of the International Search Report (PCT/ISA/210). <p>Items 13 to 20 below concern document(s) or information included:</p> <ol style="list-style-type: none"> 13. <input checked="" type="checkbox"/> An Information Disclosure Statement under 37 CFR 1.97 and 1.98. 14. <input type="checkbox"/> An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included. 15. <input type="checkbox"/> A FIRST preliminary amendment. 16. <input type="checkbox"/> A SECOND or SUBSEQUENT preliminary amendment. 17. <input type="checkbox"/> A substitute specification. 18. <input type="checkbox"/> A change of power of attorney and/or address letter. 19. <input type="checkbox"/> A computer-readable form of the sequence listing in accordance with PCT Rule 13ter.2 and 35 U.S.C. 1.821 - 1.825. 20. <input type="checkbox"/> A second copy of the published international application under 35 U.S.C. 154(d)(4). 21. <input type="checkbox"/> A second copy of the English language translation of the international application under 35 U.S.C. 154(d)(4). 22. <input type="checkbox"/> Certificate of Mailing by Express Mail 23. <input checked="" type="checkbox"/> Other items or information: PCT/IB/304/Notice of Priority/PCT/IB/308 Form PTO-1449/Amended Sheets (Pages 26 and 27) 			

U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR 1.101) <div style="font-size: 1.5em; font-weight: bold;">10/049623</div>	INTERNATIONAL APPLICATION NO. <div style="font-weight: bold;">PCT/JP00/05510</div>	ATTORNEY'S DOCKET NUMBER <div style="font-weight: bold;">219861US0PCT</div>
--	---	--

24. The following fees are submitted:				CALCULATIONS PTO USE ONLY	
BASIC NATIONAL FEE (37 CFR 1.492 (a) (1) - (5)) :					
<input type="checkbox"/> Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO and International Search Report not prepared by the EPO or JPO					
<input checked="" type="checkbox"/> International preliminary examination fee (37 CFR 1.482) not paid to USPTO but International Search Report prepared by the EPO or JPO					
<input type="checkbox"/> International preliminary examination fee (37 CFR 1.482) not paid to USPTO but international search fee (37 CFR 1.445(a)(2)) paid to USPTO					
<input type="checkbox"/> International preliminary examination fee (37 CFR 1.482) paid to USPTO but all claims did not satisfy provisions of PCT Article 33(1)-(4)					
<input type="checkbox"/> International preliminary examination fee (37 CFR 1.482) paid to USPTO and all claims satisfied provisions of PCT Article 33(1)-(4)					
ENTER APPROPRIATE BASIC FEE AMOUNT =				\$890.00	
Surcharge of \$130.00 for furnishing the oath or declaration later than months from the earliest claimed priority date (37 CFR 1.492 (e)).				<input type="checkbox"/> 20 <input type="checkbox"/> 30	
Surcharge of \$130.00 for furnishing the oath or declaration later than months from the earliest claimed priority date (37 CFR 1.492 (e)).				\$0.00	
CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE		
Total claims	9 - 20 =	0	x \$18.00	\$0.00	
Independent claims	3 - 3 =	0	x \$84.00	\$0.00	
Multiple Dependent Claims (check if applicable).				<input checked="" type="checkbox"/>	
TOTAL OF ABOVE CALCULATIONS =				\$1,170.00	
<input type="checkbox"/> Applicant claims small entity status. See 37 CFR 1.27). The fees indicated above are reduced by 1/2.				\$0.00	
SUBTOTAL =				\$1,170.00	
Processing fee of \$130.00 for furnishing the English translation later than months from the earliest claimed priority date (37 CFR 1.492 (f)).				<input type="checkbox"/> 20 <input type="checkbox"/> 30	
Processing fee of \$130.00 for furnishing the English translation later than months from the earliest claimed priority date (37 CFR 1.492 (f)).				\$0.00	
TOTAL NATIONAL FEE =				\$1,170.00	
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31) (check if applicable).				<input type="checkbox"/>	
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31) (check if applicable).				\$0.00	
TOTAL FEES ENCLOSED =				\$1,170.00	
				Amount to be: refunded	\$
				charged	\$

- a. ☒ A check in the amount of \$1,170.00 to cover the above fees is enclosed.
- b. ☐ Please charge my Deposit Account No. _____ in the amount of _____ to cover the above fees. A duplicate copy of this sheet is enclosed.
- c. ☐ The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. 15-0030 A duplicate copy of this sheet is enclosed.
- d. ☒ Fees are to be charged to a credit card. **WARNING:** Information on this form may become public. **Credit card information should not be included on this form.** Provide credit card information and authorization on PTO-2038.

NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.

SEND ALL CORRESPONDENCE TO:

Surinder Sachar
Registration No. 34,423



22850

SIGNATURE
 Norman F. Oblon
 NAME
 24,618
 REGISTRATION NUMBER
 Feb. 22 2002
 DATE

DESCRIPTION

WATER-CONTAINING POWDER COMPOSITION, PROCESS FOR PRODUCING
THE SAME, AND COSMETIC PREPARATION CONTAINING THE POWDER

5 COMPOSITION

TECHNICAL FIELD

20 The present invention relates to a composition in which
water is powderized and, more particularly, to a
water-containing powder composition that is superior in
production stability and storage stability, and releases water
when pressed with the fingers or the like during use. The
water-containing powder composition is widely utilizable in
cosmetics, foods, perfumes, agricultural chemicals, medicines,
15 and the like.

BACKGROUND ART

20 The inventors of the present invention previously
developed a water-containing powder composition that releases
water when pressed with the fingers or the like during use,
and filed a Patent application (Japanese Patent Application
laid-open No. 1993-65212). This water-containing powder
composition, prepared by a technology for powdering water and
oil using powder treated with hydrophobic silicic acid
25 anhydride and a fluorine compound, experienced problems
relating to stable production and storage stability, due to
fluctuation in the degree of hydrophobicity of the silicic acid

anhydride.

Therefore, the inventors of the present invention investigated the technology of constantly producing the water-containing powder composition with the above properties
5 by using microcapsule technology.

The inclusion of water in hydrophobic particles using microcapsule technology has been disclosed in Japanese Patent Publication 1991-67737. In this method, water is frozen, crushed into particles, and then coated with hydrophobic
10 particles.

However, it is difficult to obtain a useful microcapsule using the above method due to the following problems: ① it is difficult to obtain a fine particle diameter when the frozen water is shattered; ② the water (ice) particles easily
15 flocculate and associate during the process of shattering frozen water and coating the particles; and ③ flocculation or association of the shattered water (ice) particles tends to occur when the surface of the particles is coated.

Therefore, development of a technology for manufacturing
20 a water-containing powder composition capable of releasing water when pressed with the fingers during use by improving conventional microcapsule technology without the above manufacturing problems has been desired.

25 DISCLOSURE OF THE INVENTION

As a result of extensive studies to solve the above problems, the inventors of the present invention have

discovered that a water-containing powder with a fine particle diameter can be obtained without the problems of flocculation and association of particles by causing an aqueous phase ingredient to gel with a water-soluble gellant, forming the gel into particles each serving as a core by high speed shearing, freeze-shattering or the like, and then coating each core with hydrophobic particles. The inventors have further discovered that the obtained water-containing powder displays excellent production stability and storage stability, and maintains the characteristics of releasing water when pressed with the fingers or the like during use. These findings have led to the completion of the present invention.

Specifically, the present invention provides a water-containing powder composition comprising aqueous gel cores coated with hydrophobic particles.

The present invention further provides a process for manufacturing a water-containing powder composition comprising causing an aqueous phase ingredient to gel with a water-soluble gellant, forming the gel into particles each serving as a core by means of high speed shearing or freeze-shattering, and coating the cores with hydrophobic particles.

Furthermore, the present invention provides a cosmetic composition comprising any one of the above mentioned water-containing powder compositions and a method of applying the cosmetic compositions to the skin.

BEST MODE FOR CARRYING OUT THE INVENTION

The water-containing powder composition of the present invention has a structure wherein hydrophobic particles are coated on the exterior surface of aqueous gel cores. This
5 water-containing powder composition is manufactured by causing an aqueous phase ingredient to gel with a water-soluble gellant, forming the gel into particles, each serving as a core, by high speed shearing, freeze-shattering or the like, and then coating each core with hydrophobic particles.

10 The amount of water used in the aqueous gel of the water-containing powder composition of the present invention, is preferably 30-99.7 weight% (hereinafter indicated by %) and more preferably 40-98%. The water content in this range can provide an excellent fresh feel of water.

15 The aqueous phase ingredient for producing this aqueous gel core is an active component and other ingredients comprising water and has hydrophilic properties. As the active component, antiseptic agents such as paraoxybenzoate and phenoxy ethanol; humectants such as 1,3-butylene glycol,
20 dipropylene glycol, ethylene glycol, glycerol, and diglycerol; fresheners such as ethanol and menthol; surfactants; and other pharmacological agents such as vitamin C derivatives can be given. As the aqueous phase ingredient, an oil-in-water emulsion in which oil is emulsified and
25 dispersed in water, and a suspension with particles dispersed in water or an oil-in-water emulsion, and the like can also be used.

10049629-022300T
The water soluble gellant is an agent for gelling water by dissolving or swelling in water. For example, naturally occurring plant high polymers such as agar, guar gum, locust bean gum, quince seed gum, furcellaran, carageenan, sodium alginate, gellan gum, starch, pectin, and konjak; naturally occurring high polymers of animal origin such as gelatin; half-synthesized high polymers such as methyl cellulose, hydroxymethyl cellulose, hydroxyethyl cellulose, hydroxypropyl cellulose, carboxymethylcellulose, and cellulosic derivatives; synthesized high polymers such as polyvinyl alcohol, carboxy vinyl polymer, alkyl modified carboxy vinyl polymer, sodium polyacrylate, sodium polymethacrylate, and polyvinyl pyrrolidone; water swelling clay minerals such as magnesium sodium silicate, water-containing aluminium silicate, montmorillonite, saponite, hectolite, silicon mica tetrafluoride, and the like can be given. These may be used individually or in combination of two or more.

As the water-soluble gellant, from the viewpoint of ease in high speed shearing and freeze-shattering, and improvement in storage stability, that form hard gels with water such as agar, gelatin, carageenan, gellan gum, and magnesium sodium silicate are preferable.

In order to ensure that a sufficient amount of aqueous phase ingredient can be acquired, the content of the water-soluble gellant used in the present invention is preferably 0.1-10% of the aqueous gel, varying depending on

the type of water-soluble gellant used.

When the water-soluble gellant of the present invention is a compound requiring a counter-alkali for gelling water, such as carboxy vinyl polymer, alkyl modified carboxy vinyl polymer, and the like, sodium hydroxide, potassium hydroxide, triethanolamine, diethanolamine, and the like may be used. In this instance, depending on the type of water-soluble high polymer used, the ratio of the water-soluble gellant and the alkali is preferably 1:0.001-1:1.

In the present invention, as methods for producing a powdered aqueous gel core using an aqueous gel composed of an aqueous phase ingredient and a water soluble gellant, high speed shearing, freeze-shattering, and the like can be given. As the method of high speed shearing, a high speed pin mill, cutter-mixer, and the like can be given. As a method of freeze shattering, freezing of the aqueous gel using a refrigerant such as liquid nitrogen and then crushing the aqueous gel can be given. For the temperature used during freeze-shattering of the aqueous gel, -20°C to -190°C is preferable depending on the hardness and coagulating point of the aqueous gel. The particle size after freeze-shattering is preferably between about 1 μm and 300 μm .

The hydrophobic particles used to coat the powdered particles of the aqueous gel obtained in this manner function to improve anti-aggregation and storage stability by adhering to or being adsorbed onto the surface. As these hydrophobic particles, particles exhibiting hydrophobicity, hydrophilic

particles that are surface treated using a known hydrophobicizing agent, hydrophobic particles further treated using a hydrophobicizing agent to increase the degree of hydrophobicity, and the like can be used. The particle diameter of these hydrophobic particles must be smaller than the particle diameter of the powdered particles of the aqueous gel. A particle diameter 1/10 or less of the particle diameter of the aqueous gel powdered particles is preferable from the viewpoint of coating efficiency of the surface.

Among the hydrophobic particles used in the present invention, as examples of the particles having hydrophobicity, polystyrene powder, polyethylene powder, organopolysiloxane elastomer powder, polymethylsilsesquioxane powder, N-acyl-lysine, polyethylene tetrafluoride resin powder, acrylic resin powder, epoxy resin powder, nylon powder, aluminum stearate, zinc laurate, and magnesium stearate can be given. These particles may be used individually or in combination of two or more.

A hydrophobic powder prepared by treating the surface of a hydrophilic powder with a hydrophobicizing agent can also be used. As the hydrophobicizing agent, organic silicon compounds such as trimethylsilylation agent and methylhydrodiene polysiloxane, fluorine compounds such as perfluoropolyether alkyl phosphate and perfluoropolyether silane, metallic soaps, oil agents, and the like can be given. These agents may be used individually or in combination of two or more. Of these, organic silicon compounds and fluorine

compounds are preferable due to the improvement in the degree of hydrophobicity. As the hydrophilic particles, for example, inorganic particles such as titanium oxide, zinc oxide, silicic acid anhydride, aluminium oxide, magnesium oxide, zirconium oxide, magnesium carbonate, calcium carbonate, aluminium silicate, magnesium silicate, magnesium aluminium silicate, mica, synthetic mica, synthetic sericite, sericite, talc, silicon carbide, barium sulfate, boron nitride, bismuth oxychloride, and mica titanium; organic particles such as silk powder, starch, and cellulose crystal; and composite particles such as mica titanium coated with titanium oxide powder, zinc oxide powder, or barium sulfate can be given. These hydrophilic particles surface treated with a hydrophobicizing agent may be used individually or in combination of two or more.

Of the above-mentioned hydrophobic particles, fumed silicic acid anhydride treated by a hydrophobicizing agent with an average particle diameter of 0.001-0.1 μm is particularly preferable due to the increase in storage stability. As commercially available products of these hydrophobic particles, AEROSIL R974, R972, RX200, RX300 (manufactured by Nippon Aerosil Co., Ltd.), CAB-O-SIL TS-530 (manufactured by Cabot Corporation), and the like can be given. In the water-containing powder composition of the present invention, a preferable mass ratio of the aqueous gel powder and hydrophobic particles is approximately 100:0.5-100:25, although such a ratio varies according to the particle diameter of the aqueous gel powder and the hydrophobic particles.

There are no particular limitations to the method of coating the surface of the aqueous gel powder with the hydrophobic particles. One example of such a method of coating comprises placing the hydrophobic particles in a stirring vessel and adding the aqueous gel powder while stirring at a low temperature to prevent fusion or aggregation due to a rise in temperature. The stirring vessel used preferably has a jacket with a cooling mechanism and stirring blades that rarely come in contact with the wall and bottom of the jacket.

In the cosmetic preparation of the present invention, the content of the above water-containing powder composition is preferably 10-100%, and more preferably 30-90%. When this range is used, a cosmetic preparation exhibiting particularly superior freshness and a refreshing feeling, which are the effects attainable by the addition of water, can be obtained.

In addition to the above water-containing powder composition, various additives conventionally used in cosmetic preparations can be added to the cosmetic preparation containing the water-containing powder composition of the present invention to the extent the effect is not adversely affected. Such additives include powders, oil agents; surfactants; oil gelling agents such as partially cross-linked organopolysiloxane and dextrin fatty acid esters; UV absorbers; oil soluble film-forming agents such as acryl-modified silicone and trimethylsiloxysilicate; solvents such as ethanol; antiseptic agents such as para-oxybenzoic acid derivatives and phenoxyethanol;

vitamins; antiphlogistines; antioxidants; chelating agents; pharmacological agents such as vitamin C derivatives; humectants such as glycol; water; water soluble high polymers; polyhydric alcohols; refreshers; and perfumes.

5 Of the powders that can be added to the cosmetic preparation of the present invention, those normally added to cosmetic compositions for the purpose of coloring effect, makeup effect, ultra-violet radiation shielding effect, and feel adjustment effect such as inorganic particles,
10 photoluminescent particles, organic particles, pigment particles, and composite particles, with no limitations to particle shape, size, and structure, can be given. These particles may be used individually or in combination of two or more. Specifically, inorganic particles such as titanium
15 oxide, ferric ferrocyanide, ultramarine, red iron oxide, yellow iron oxide, black iron oxide, zinc oxide, aluminium oxide, silica, magnesium oxide, zirconium oxide, magnesium carbonate, calcium carbonate, chromium oxide, chromium hydroxide, carbon black, aluminium silicate, magnesium
20 silicate, magnesium aluminium silicate, mica, synthetic mica, synthetic sericite, sericite, talc, kaolin, silicon carbide, barium sulfate, bentonite, smectite, boron nitride, and the like; photoluminescent particles such as bismuth oxychloride, mica titanium, iron oxide coated mica, iron oxide, titanium
25 oxide, organic pigment-treated mica titanium, aluminum powder, and the like; organic particles such as nylon powder, polymethyl methacrylate, acrylonitrile-methacrylate

copolymer powder, vinylidene chloride-methacrylic acid
copolymer powder, polyethylene powder, polystyrene powder,
organopolysiloxane elastomer powder,
polymethylsilsesquioxane powder, polytetrafluoroethylene
5 powder, wool powder, silk powder, cellulose crystal, magnesium
stearate, zinc stearate, N-acyl-lysine, and the like; pigment
particles such as organic tar type pigment, lake pigment, and
the like; and composite particles such as mica titanium coated
with titanium oxide powder, zinc oxide powder, barium sulfate,
10 titanium oxide containing silica dioxide, zinc oxide
containing silica dioxide, and the like can be given. These
particles may be used individually or in combination of two
or more.

Composite powders made from two or more of the above
15 particles may be used. In addition, particles with the surface
treated by a fluorine compound, silicon containing oil agent,
metallic soap, wax, surfactant, fat, oil, hydrocarbon, or the
like by a conventional method may also be used. The amount
of these particles incorporated in the cosmetic preparation
20 of the present invention is preferably 1-90%, although the
specific amount varies depending on the purpose of adding the
particles and the type of cosmetic preparation.

Oil agents added to conventional cosmetic preparations
with the purpose of improving adhesion to the skin, providing
25 emollience, and improving makeup durability may be used in the
cosmetic preparation of the present invention. Such oil
agents include hydrocarbons, fats and oils, waxes, hardened

oils, ester oils, fatty acids, higher alcohols, silicone oils, fluorine-containing oils, and lanolin derivatives, regardless of the origin (animal oils, vegetable oils, or synthetic oils) and the state (solid, half-solid, liquid, or volatile).

- 5 Specific examples of such oil agents include hydrocarbons such as paraffin wax, ceresin wax, ozokerite, microcrystalline wax, Japanese tallow, montan wax, fisher tropsch wax, polyethylene wax, liquid paraffin, petroleum jelly, squalane, and the like; natural products such as carnauba wax, beeswax, lanolin wax, candelila, and the like; esters such as glyceryl tribehenate, pentaerythritol colophonate, pentaerythritol rhodinate, isopropyl myristate, dialkyl carbonate, glyceryl trioctanoate, diglyceryl tri-isostearate, and the like; alkyl modified silicones such as stearyl siloxane and the like; fatty acids
- 10 such as stearic acid, 12-hydroxy stearic acid, behenic acid, oleic acid, and the like; higher alcohols such as cetanol, stearyl alcohol, behenyl alcohol, and the like; fats and oils such as olive oil, castor oil, jojoba oil, mink oil, and the like; lanolin derivatives such as isopropyl lanolin fatty acid,
- 15 lanolin alcohol, and the like; silicone oils such as dimethyl polysiloxane, methylphenyl polysiloxane, and the like; cyclic silicones such as decamethyl cyclopentasiloxane, octamethyl cyclotetrasiloxane, and the like; polyoxyalkylene modified and alkyl modified silicone oils; fluorine-containing oils
- 20 such as perfluorodecane, perfluorooctane, and the like. These oil agents may be used individually or in combination of two or more.

The amount of these oil agents used in the cosmetic preparation of the present invention is preferably 0.1-50%, although the specific amount varies depending on the purpose of addition and the type of cosmetic preparation.

5 The cosmetic preparation incorporating the water-containing powder composition of the present invention includes, but is not limited to, makeup such as eye color, foundation, rouge, face powder, skin care cosmetic preparations such as body powder, anti-perspirant powder, 10 whitening powder, milky lotion, cream, beauty lotion, and sunscreen lotion.

 The cosmetic preparation of the present invention explained above containing a water-containing powder composition which breaks and releases water when applied with 15 the fingers, palm of the hand, sponge, or chip applicator possesses the characteristics of refreshing feeling and film forming during use.

 The water-containing powder composition of the present invention has excellent production stability and storage 20 stability, breaks and releases water when applied with the fingers, palm of the hand, sponge, or chip applicator. The cosmetic preparation including the water-containing powder composition of the present invention, though having a powdery and solid appearance, easily breaks to release water thereby 25 having refreshing feeling and film forming characteristics that cannot be obtained in conventional cosmetic preparations. Also, in addition to cosmetics, the water-containing powder

composition of the present invention can be used in a broad range of products including foods, perfumes, agricultural chemicals, and medicines.

5 EXAMPLES

The present invention will be described in more detail by way of Examples which should not be construed as limiting the present invention.

10 Example 1

Water-containing powder composition:

Water-containing powder compositions were prepared in the following manner from the components shown in Table 1. The water-containing powder compositions thus prepared were
15 evaluated for "production stability", "storage stability", and "ease of collapsing and releasing water under finger pressure during use" in the following manner. The results are shown in Table 2.

(Composition)

Table 1

Table 1	Present Invention										(weight%) Comparative Example
	1	2	3	4	5	6	7				
1. Purified water	Balance	Balance	Balance	Balance	Balance	Balance	Balance	Balance	Balance	Balance	
2. Agar	0.2	2	2	-	-	-	-	1	-	-	
3. Gelatin	-	-	-	3	-	-	-	-	-	-	
4. Carageenan	-	-	-	-	0.05	0.05	-	-	-	-	
5. Starch	-	-	-	0.2	-	-	-	-	-	-	
6. Carboxy vinyl polymer	-	-	-	-	0.7	-	-	-	-	-	
7. Magnesium sodium silicate *1	-	-	-	-	-	-	-	10	-	-	
8. Alkyl modified carboxy vinyl polymer *2	-	-	-	-	-	0.5	-	-	-	-	
9. Glycerol	2	2	2	2	2	2	2	2	2	2	
10. 1,3-Butylene glycol	10	10	10	10	10	10	10	10	10	10	
11. Antiseptic agent	Appropriate amount	Appropriate amount	Appropriate amount	Appropriate amount	Appropriate amount	Appropriate amount	Appropriate amount	Appropriate amount	Appropriate amount	Appropriate amount	
12. Triethanol amine	-	-	-	-	0.7	0.5	-	-	-	-	
13. Liquid paraffin	-	-	-	-	-	5	-	-	-	-	
14. Talc	-	-	-	-	3	-	-	-	-	-	
15. Soybean phospholipid	-	-	-	-	0.3	-	-	-	-	-	
16. Perfume	Appropriate amount	Appropriate amount	Appropriate amount	Appropriate amount	Appropriate amount	Appropriate amount	Appropriate amount	Appropriate amount	Appropriate amount	Appropriate amount	
17. Hydrophobicized silicic acid anhydride *3	3	3	25	-	-	-	-	-	-	-	
18. Hydrophobicized silicic acid anhydride *4	-	-	-	3	3	3	3	3	3	3	

*1: Laponite XLG (manufactured by Laponite Co., Ltd.)

*2: Carbopol 1342 (manufactured by Goodrich Chemical Co., Ltd.)

*3: AEROSIL R972 (dimethyl dichlorosilane treated silicic acid anhydride manufactured by Nippon Aerosil Co., Ltd.)

*4: AEROSIL RX300 (hexamethyl disilazane treated silicic acid anhydride manufactured by Nippon Aerosil Co., Ltd.)

(Method of preparation)

- A. The components 1-12 are mixed and dissolved (or swelled).
- B. The components 13-16 are added to A and are mixed by dispersion.
- C. B is cooled to -80°C using liquefied nitrogen and freeze-shattered to obtain an aqueous gel powder with a particle diameter of $80\text{ }\mu\text{m}$.
- D. C is added to and mixed with the component 17 or 18 in a stirring vessel while stirring to obtain a water-containing powder composition.

(Method of evaluation)

Production Stability:

The water-containing powder composition was prepared five times under the same conditions and the fluctuation of the particle diameter was evaluated according to the following standard.

Evaluation Standard

- ⊙ Completely uniform with no fluctuation
- Nearly uniform with slight fluctuation
- △ Fluctuation is present
- × Fluctuation is significant

Storage stability:

The water-containing powder composition was stored at 40°C for six months and then evaluated according to the following standards.

Evaluation Standard

- ◎ No change in outward appearance after storage
- Slight association of the particles is noticeable
- △ Association of the particles is noticeable
- 5 × Water separation is noticeable

Ease of collapsing and releasing water under finger pressure during use:

Each water-containing powder composition was pressed with the fingers, and the condition of water release was
10 evaluated according to the following standards.

Evaluation Standard

- ◎ The composition immediately collapses and releases water
- Although slightly difficult to collapse, the
15 composition releases water
- △ Although difficult to collapse, the composition releases water
- × The composition collapses and releases water with difficulty

20 (Results)

Table 2

	Production stability	Storage stability	Ease of collapsing and releasing water during use
Example 1	○	○	○
Example 2	◎	◎	◎
Example 3	○	◎	○
Example 4	◎	◎	◎
Example 5	○	○	○
Example 6	○	○	○
Example 7	○	○	○
Comparative Example 1	△	×	○

As is clear from Table 2, the water-containing powder compositions 1-7 of the present invention have excellent "production stability", "storage stability", and "ease of collapsing and releasing water under finger pressure during use" in comparison to the Comparative Example.

10 Example 2

Water-containing powder composition:

Water-containing powder compositions were prepared from the following components using the following method. The water-containing powder compositions prepared were evaluated as ◎ for "production stability", "storage stability", and "ease of collapsing and releasing water under finger pressure during use" under the same conditions in Example 1.

	(Component)	weight%
	1. Purified water	balance
	2. Agar	1
	3. Magnesium sodium silicate * ¹	5
5	4. Glycerol	2
	5. 1,3-butylene glycol	10
	6. Antiseptic agent	appropriate amount
	7. Triethanol amine	1
10	8. Stearic acid	2
	9. Glycol monostearic acid	1
	10. Cetanol	1
	11. Dimethyl polysiloxane	1
	12. Liquid paraffin	5
15	13. 2-ethylhexyl paramethoxy cinnamic acid	1
	14. Sorbitan sesquioleate	0.5
	15. Polyoxyethylene sorbitan monooleate	0.5
	16. Nylon powder	1
20	17. Perfume	appropriate amount
	18. hydrophobic treated silicic acid anhydride * ⁴	3
	(Method of preparation)	
25	A. The components 1-7 are mixed (or swelled) in a solution.	
	B. The components 8-15 are heated, dissolved, added to A, and emulsified.	

C. The components 16-17 are added and mixed by dispersion.

D. C is cooled to -120°C using liquefied nitrogen, and freeze-shattered to obtain an aqueous gel powder with a particle diameter of 80 μm .

5 E. D is added to and mixed with the component 18 in a stirring vessel while stirring to obtain a water-containing powder composition.

Example 3

10 Deodorant powder:

(Component)	weight%
-------------	---------

1. Aluminum hydroxychloride	20
-----------------------------	----

2. Purified water	balance
-------------------	---------

3. Agar	3
---------	---

15 4. Propylene glycol	5
------------------------	---

5. Polyoxyethylene (20 mol) oleyl ether	0.5
---	-----

6. Ethyl alcohol	5
------------------	---

7. Hemlock benzal chloride	0.2
----------------------------	-----

8. Perfume	0.3
------------	-----

20 9. Hydrophobic treated silicic acid	5
--	---

anhydride *⁴

(Method of preparation)

A. 1-4 are mixed and dissolved.

B. 5-8 are mixed and dissolved.

25 C. A is added to B and solubilized.

D. C is powderized using a Henschel mixer (manufactured by Mitsui Miike Chemical Industry Co., Ltd.).

E. D is added to and mixed with 9 to obtain a deodorant powder.

Example 4

5 Wine powder:

(Component)	weight%
-------------	---------

1. Purified water	10
-------------------	----

2. Agar	1
---------	---

3. Wine	80
---------	----

10 4. Silicic acid anhydride treated	3
--------------------------------------	---

with magnesium stearate

(Method of preparation)

A. 1-2 are heated and dissolved, 3 is added and mixed.

B. A is cooled to -80 to -100°C and then freeze-shattered.

15 C. B is added to and mixed with 4 to obtain a wine powder.

Preparation Example 1

Water-containing powder composition (foundation):

(Component)	weight%
-------------	---------

20 1. Titanium oxide treated with	5
-----------------------------------	---

fluorine compound *⁵

2. Bengala treated with fluorine	0.1
----------------------------------	-----

compound *⁵

3. Yellow iron oxide fluorine	1
-------------------------------	---

25 compound *⁵

4. Black iron oxide fluorine	0.05
------------------------------	------

compound *⁵

5. Sericite treated with silicon *⁶ balance
6. Talc treated with silicon *⁶ 10
7. Water-containing powder 70

composition of Example 1

- 5 *⁵: powder treated with 5% perfluoroalkyl phosphate
 *⁶: powder treated with 3% methyl hydrodiene polysiloxane

Preparation Example 2

Water-containing powder composition (eye shadow)

- | | | |
|----|---|---------------|
| 10 | (Component) | weight% |
| | 1. Water-containing powder | balance |
| | composition of Example 1 | |
| | 2. Partially cross-linked | 2 |
| | organopolysiloxane swelling | |
| 15 | material * ⁸ | |
| | 3. Dimethyl polysiloxane | 1 |
| | 4. Silicon treated silicic acid | 5 |
| | anhydride * ⁶ | |
| | 5. Silicone treated red pigment | 0.3 |
| 20 | no. 202 * ⁶ | |
| | 6. Yellow iron oxide | 1 |
| | 7. Titanium mica treated with | 5 |
| | fluorine compound * ⁵ | |
| | 8. Talc treated with metallic soap * ⁹ | 10 |
| 25 | 9. Titanium oxide | 1 |
| | 10. Antiseptic agent | proper amount |

*⁸: silicon KSG-18 (manufactured by Shin-Etsu Chemical

Co., Ltd.)

*⁹: powder treated with 3% zinc laurate

Preparation Example 3

5 Water-containing powder composition (beauty lotion)

(Component)	weight%
1. Water-containing powder	balance
composition of Example 2	
2. Cane sugar fatty acid ester	1
10 3. Dipropylene glycol	1
4. Polystyrene powder	3
5. Antiseptic agent	appropriate amount

15 Preparation Example 4

Water-containing powder composition (whitening powder):

(Component)	weight%
1. Water-containing powder	balance
composition of Example 1	
20 2. Ascorbic acid magnesium phosphate	1
3. Ascorbic acid sodium phosphate	1
4. Diglycerine	0.5
5. Hydrogenated soybean phospholipid	1
6. Squalane	2
25 7. Dextrin fatty acid ester	0.3
8. Nylon powder treated with fluorine	3
compound * ⁵	

- | | |
|----------------------|-----------------------|
| 9. Perfume | appropriate
amount |
| 10. Antiseptic agent | appropriate
amount |

5 *⁵: powder treated with 5% perfluoroalkyl phosphate

Preparation Example 5

Water-containing powder composition (sunscreen)

	(Component)	weight%
10	1. Water-containing powder composition of Example 2	balance
	2. Titanium oxide particles treated with fluorine compound * ⁵	2
	3. Silicon treated zinc oxide particles * ⁶	1
15	4. 2-Triglyceryl ethyl hexanoic acid	1
	5. 4-Tert-butyl-4'-methoxy dibenzoylmethane	0.05
	6. Alkyl polyacrylate powder	5
20	7. Perfume	appropriate amount
	8. Antiseptic agent	appropriate amount

*⁵: powder treated with 5% perfluoroalkyl phosphate

25 *⁶: powder treated with 3% methyl hydrodiene polysiloxane

Preparation Example 6

Water-containing powder composition (body powder)

(Component)	weight%
-------------	---------

1. Water-containing powder	balance
----------------------------	---------

5 composition of Example 3

2. 1-Menthol	0.05
--------------	------

3. Camphor	0.05
------------	------

4. Ethanol	2
------------	---

5. Silicic anhydride	10
----------------------	----

10 6. Antiseptic agent	appropriate amount
------------------------	-----------------------

WHAT IS CLAIMED IS:

1. (amended) A water-containing powder composition comprising aqueous gel cores, obtained by gelling an aqueous phase ingredient with a water-soluble gellant, coated with hydrophobic particles, wherein the aqueous gellant is one or more components selected from the group consisting of agar, gelatin, carageenan, gellan gum, and magnesium sodium silicate.

2. (amended) The water-containing powder composition of claim 1, wherein the aqueous gel cores are obtained by gelling an aqueous phase ingredient with a water-soluble gellant, which is one or more components selected from the group consisting of agar, gelatin, carageenan, gellan gum, and magnesium sodium silicate, and freeze-shattering the gel.

3. The water-containing powder composition of claim 1 or claim 2, wherein the hydrophobic particles have a particle diameter of 1/10 or less of the particle diameter of the aqueous gel cores.

4. (Deleted)

5. (amended) The water-containing powder composition of any one of claims 1-3, wherein the cores obtained from the aqueous gel are powdered gel cores.

6. (amended) A process for manufacturing a water-containing powder composition comprising gelling an aqueous phase ingredient with a water-soluble gellant, which is one or more components selected from the group consisting of agar, gelatin, carageenan, gellan gum, and magnesium sodium silicate, to form aqueous gel cores, and coating the aqueous gel cores with hydrophobic particles.

7. The process for manufacturing the water-containing powder composition of claim 6, wherein the aqueous phase ingredient caused to gel using a water-soluble gellant is formed into powdered aqueous gel cores by freeze-shattering.

8. A cosmetic preparation comprising the water-containing powder composition according to any one of claims 1 to 5.

9. A method of applying makeup, comprising applying the cosmetic preparation of claim 8 to the skin and applying pressure to cause water to release from said composition.

ABSTRACT OF THE DISCLOSURE

A water-containing powder composition comprising particles each composed of an aqueous gel as a core and
5 hydrophobic particles with which the core is coated; and a process for producing the water-containing powder composition which comprises causing an aqueous phase ingredient to gel with a water-soluble gellant, forming the gel into particles each serving as a core, and then coating each core with hydrophobic
10 particles.

The composition is characterized in that it is excellent in production stability and storage stability and that the gel-based particles break to release water when used and pressed with, e.g., fingers. The water-containing powder
15 composition is widely utilizable in cosmetics, foods, perfumes, agricultural chemicals, medicines, etc.

Declaration and Power of Attorney For Patent Application

特許出願宣言書及び委任状

Japanese Language Declaration

日本語宣言書

下記の氏名の発明者として、私は以下の通り宣言します。

私の住所、私書箱、国籍は下記の私の氏名の後に記載された通りです。

下記の名称の発明に関して請求範囲に記載され、特許出願している発明内容について、私が最初かつ唯一の発明者（下記の氏名が一つの場合）もしくは最初かつ共同発明者（下記の名称が複数の場合）であると信じています。

上記発明の明細書は、

- ☐ 本書に添付されています。
- ☐ ____月____日に提出され、米国出願番号または特許協定条約国際出願番号を____とし、
(該当する場合) _____に訂正されました。

私は、特許請求範囲を含む上記訂正後の明細書を検討し、内容を理解していることをここに表明します。

私は、連邦規則法典第37編第1条56項に定義されるとおり、特許資格の有無について重要な情報を開示する義務があることを認めます。

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled.

WATER-CONTAINING POWDER COMPOSITION, PROCESS

FOR PRODUCING THE SAME, AND COSMETIC PREPARATION

CONTAINING THE POWDER COMPOSITION

the specification of which

- ☐ is attached hereto.
- ☒ was filed on August 17, 2000
as United States Application Number or
PCT International Application Number
PCT/JP00/05510 and was amended on
July 16, 2001 (if applicable).

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, Section 1.56.

Japanese Language Declaration
(日本語宣言書)

私は、米国法典第35編119条 (a) - (d) 項又は365条 (b) 項に基づき下記の、米国以外の国の少なくとも一カ国を指定している特許協力条約365 (a) 項に基づく国際出願、又は外国での特許出願もしくは発明者証の出願についての外国優先権をここに主張するとともに、優先権を主張している、本出願の前に出願された特許または発明者証の外国出願を以下に、枠内をマークすることで、示しています。

Prior Foreign Application(s)
外国での先行出願

<u>237149/1999</u> (Number) (番号)	<u>Japan</u> (Country) (国名)
<u>172172/2000</u> (Number) (番号)	<u>Japan</u> (Country) (国名)

私は、第35編米国法典119条 (e) 項に基づいて下記の米国特許出願規定に記載された権利をここに主張いたします。

<u>(Application No.)</u> (出願番号)	<u>(Filing Date)</u> (出願日)
------------------------------------	-------------------------------

私は、下記の米国法典第35編120条に基づいて下記の米国特許出願に記載された権利、又は米国を指定している特許協力条約365条 (c) に基づく権利をここに主張します。また、本出願の各請求範囲の内容が米国法典第35編112条第1項又は特許協力条約で規定された方法で先行する米国特許出願に開示されていない限り、その先行米国出願書提出日以降で本出願書の日本国内または特許協力条約国際提出日までの期間中に入手された、連邦規則法典第37編1条56項で定義された特許資格の有無に関する重要な情報について開示義務があることを認識しています。

<u>(Application No.)</u> (出願番号)	<u>(Filing Date)</u> (出願日)
<u>(Application No.)</u> (出願番号)	<u>(Filing Date)</u> (出願日)

私は、私自信の知識に基づいて本宣言書で私が行なう表明が真実であり、かつ私の入手した情報と私の信じているところに基づく表明が全て真実であると信じていること、さらに故意になされた虚偽の表明及びそれと同等の行為は米国法典第18編第1001条に基づき、罰金または拘禁、もしくはその両方により処罰されること、そしてそのような故意による虚偽の声明を行えば、出願した、又は既に許可された特許の有効性が失われることを認識し、よってここに上記のごとく宣誓を致します。

I hereby claim foreign priority under Title 35, United States Code, Section 119 (a)-(d) or 365(b) of any foreign application(s) for patent or inventor's certificate, or Section 365(a) of any PCT International application which designated at least one country other than the United States, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate, or PCT International application having a filing date before that of the application on which priority is claimed.

<u>24/August/1999</u> (Day/Month/Year Filed) (出願年月日)	<u>Priority Claimed</u> 優先権主張
<u>08/June/2000</u> (Day/Month/Year Filed) (出願年月日)	<input checked="" type="checkbox"/> Yes はい
	<input type="checkbox"/> No いいえ

I hereby claim the benefit under Title 35, United States Code, Section 119(e) of any United States provisional application(s) listed below.

<u>(Application No.)</u> (出願番号)	<u>(Filing Date)</u> (出願日)
------------------------------------	-------------------------------

I hereby claim the benefit under Title 35, United States Code, Section 120 of any United States application(s), or Section 365(c) of any PCT International application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of Title 35, United States Code Section 112, I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, Section 1.56 which became available between the filing date of the prior application and the national or PCT International filing date of application.

<u>(Status: Patented, Pending, Abandoned)</u> (現況：特許許可済、係属中、放棄済)
<u>(Status: Patented, Pending, Abandoned)</u> (現況：特許許可済、係属中、放棄済)

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Japanese Language Declaration
(日本語宣言書)

委任状：私は下記の発明者として、本出願に関する一切の手続きを米特許商標局に対して遂行する弁理士または代理人として、下記の者を指名いたします。
(弁理士、または代理人の指名及び登録番号を明記のこと)

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith: (list name and registration number)

Norman F. Oblon, Reg. No. 24,618; Marvin J. Spivak, Reg. No. 24,913; C. Irvin McClelland, Reg. No. 21,124; Gregory J. Maier, Reg. No. 25,599; Arthur I. Neustadt, Reg. No. 24,854; Richard D. Kelly, Reg. No. 27,757; James D. Hamilton, Reg. No. 28,421; Eckhard H. Kuesters, Reg. No. 28,870; Robert T. Pous, Reg. No. 29,099; Charles L. Gholz, Reg. No. 26,395; William E. Beaumont, Reg. No. 30,996; Jean-Paul Lavalleye, Reg. No. 31,451; Stephen G. Baxter, Reg. No. 32,884; Richard L. Treanor, Reg. No. 36,379; Steven P. Wehrhouch, Reg. No. 32,829; John T. Goolkasian, Reg. No. 26,142; Richard L. Chinn, Reg. No. 34,305; Steven E. Lipman, Reg. No. 30,011; Carl E. Schlier, Reg. No. 34,426; James J. Kulbaski, Reg. No. 34,648; Richard A. Nerfeld, Reg. No. 35,299; J. Derek Mason, Reg. No. 35,270; Surinder Sachar, Reg. No. 34,423; Jeffrey B. McIntyre, Reg. No. 36,867; William T. Enos, Reg. No. 33,128; Michael E. McCabe, Jr., Reg. No. 37,182; Bradley D. Lytle, Reg. No. 40,073; and Michael R. Casey, Reg. No. 40,294, with full powers of substitution and revocation.

書類送付先

Send Correspondence to:

OBLON, SPIVAK, MCCLELLAND, MAIER & NEUSTADT, P.C.
FOURTH FLOOR
1755 JEFFERSON DAVIS HIGHWAY
ARLINGTON, VIRGINIA 22202 U.S.A.

直接電話連絡先：(名前及び電話番号)

Direct Telephone Calls to: (name and telephone number)

(703) 413-3000

単独発明者または第一の共同発明者の氏名	Full name of sole or first joint inventor Yoichiro TANAKA
発明者の署名	Inventor's signature Yoichiro Tanaka
日付	Date 13/FEB/2002
住所	Residence c/o KOSE Corporation, 48-18, Sakae-cho, Kita-ku, Tokyo 114-0005, Japan JPX
国籍	Citizenship Japanese
郵便の宛先	Post Office Address same as above
第二の共同発明者の氏名	Full name of second joint inventor, if any Yuriko TOMITA
第二の共同発明者の署名	Second joint inventor's signature Yuriko Tomita
日付	Date 13/FEB/2002
住所	Residence c/o KOSE Corporation, 48-18, Sakae-cho, Kita-ku, Tokyo 114-0005, Japan JPX
国籍	Citizenship Japanese
郵便の宛先	Post Office Address same as above

(第三以降の共同発明者についても同様に記載し、署名すること)

(Supply similar information and signature for third and subsequent joint inventors.)

Japanese Language Declaration

(日本語宣言書)

3.00

第三の共同発明者の氏名	Full name of third joint inventor, if any Shinji KOBAYASHI
第三の共同発明者の署名	Third joint Inventor's signature Shinji Kobayashi
日付	Date 13/FEB/2002
住所	Residence c/o KOSE Corporation, 48-18, Sakae-cho, Kita-ku, Tokyo 114-0005, Japan
国籍	Citizenship Japanese
郵便の宛先	Post Office Address same as above

第四の共同発明者の氏名	Full name of fourth joint inventor, if any
第四の共同発明者の署名	Fourth joint Inventor's signature
日付	Date
住所	Residence
国籍	Citizenship
郵便の宛先	Post Office Address

第五の共同発明者の氏名	Full name of fifth joint inventor, if any
第五の共同発明者の署名	Fifth joint Inventor's signature
日付	Date
住所	Residence
国籍	Citizenship
郵便の宛先	Post Office Address

第六の共同発明者の氏名	Full name of sixth joint inventor, if any
第六の共同発明者の署名	Sixth joint Inventor's signature
日付	Date
住所	Residence
国籍	Citizenship
郵便の宛先	Post Office Address

(第六またはそれ以降の共同発明者に対しても同様な情報および署名を提供すること。)

(Supply similar information and signature for third and subsequent joint inventors.)